



Study of atomic motion in rubidium borate glasses

C. Tietz^{*1}, M. Ross¹, M. Stana¹ and B. Sepiol¹

¹Universität Wien, Fakultät für Physik, Strudlhofgasse 4, 1090 Wien, Austria *christoph.tietz@univie.ac.at

Introduction


Atomic Scale X-ray Photon Correlation Spectroscopy (aXPCS) uses coherent X-rays to probe the dynamics of materials on an atomic scale. It was applied to study atomic diffusion in crystals [1], but its application was recently extended to glasses as well [2]. Results of dynamics and Small-Angle X-ray Scattering (SAXS) studies on high- and low-alkali content rubidium borate glasses are presented here.

Theory


Real space structure: changes in time results in different scattering patterns Sequence of scattering patterns \rightarrow Time correlation

Functional form of the ACF:

 $g^{(2)}(q) = 1 + \beta e^{-\left(\frac{2\Delta t}{\tau}\right)^{\alpha}}$




Space and time dependence described by the Van Hove Pair Correlation Function



Intensity Auto Correlation Function (ACF)


$$g^{(2)}(\vec{q},\Delta t) := \frac{\langle I(\vec{q},t)I(\vec{q},t+\Delta t)\rangle}{\langle I(\vec{q},t)\rangle^2}$$




Normalization by the total structure factor

$$\tau_{coh}(\vec{q})^{-1} = \frac{\tau_{inc}(\vec{q})^{-1}}{S_{total}(q)}$$

Results: fit to jump models




SAXS



SAXS intensities as a function of momentum transfer





Conclusion

- Diffusion in low rubidium content borate glasses best described by two-jump model
- Large difference in diffusivity between low and high alkali glass
- Diffusion at 20K still too fast to be measured in high alkali glass
- Inhomogenities are much larger in high alkali sample

[1] M. Leitner, B. Sepiol, L. M. Stadler, S. Pfau and G. Vogl, Nat. Mater, 8 (2009), 717.[2] M. Ross, M. Stana, M. Leitner and B. Sepiol, New J. Phys. 16 (2014) 093042.

This work was funded by the FWF (Austrian Science Fund), Project P-28232.



Der Wissenschaftsfonds.